

**Table 6 Crack Movement Reading**

NO	PIER NO	REF POINTS	Crack width (mm)	CRACK MOVEMENT (mm)							
				28/4/2011	5/5/2011	12/5/2011	19/5/2011	26/5/2011	2/6/2011	9/6/2011	16/6/2011
1	P 1-33	1A	1.2	0.00	0.10	0.13	0.13	0.10	0.10	0.13	0.07
2		1B	4.5	0.00	-0.01	0.13	0.13	0.10	0.10	0.04	0.08
3		2A	0.2	0.00	0.02	0.05	0.05	0.06	0.03	0.04	0.00
4		2B	0.3	0.00	-0.03	-0.03	-0.03	0.00	0.06	-0.02	-0.06
5		3A	2.0	0.00	0.05	0.05	0.05	0.07	0.06	0.08	0.05
6		3B	2.0	0.00	0.00	0.02	0.02	0.02	0.00	0.01	-0.02
7	P 1-25	4A	0.15	0.00	0.02	0.02	0.09	0.03	0.01	0.02	0.00
8		4B	0.2	0.00	0.02	0.03	0.09	0.13	0.10	0.02	-0.01
9		5A	0.2	0.00	0.23	0.24	0.21	0.25	0.22	0.24	0.21
10		5B	0.15	0.00	0.03	0.02	0.08	-0.01	-0.05	-0.03	-0.04
11	P 1-15B	6A	0.15	0.00	0.05	0.05	0.09	0.04	0.04	0.04	0.01
12		6B	0.15	0.00	0.04	0.04	0.07	0.02	0.03	0.03	0.00
13	P 1-14B	7A	0.15	0.00	0.03	0.04	0.06	0.03	0.02	0.04	0.01
14		7B	0.2	0.00	0.03	0.04	0.07	0.04	0.13	0.03	0.01
15	P 1-13B	8A	0.2	0.00	0.02	0.04	0.05	0.04	0.01	0.04	0.01
16		8B	0.1	0.00	-0.03	-0.02	0.00	-0.02	-0.03	-0.01	-0.04
17		9A	0.2	0.00	0.03	0.04	0.05	0.03	0.01	0.04	0.01
18		9B	0.35	0.00	0.04	0.06	0.08	0.04	0.04	0.07	0.03
19		10A	0.1	0.00	0.05	0.06	0.09	0.08	0.07	0.26	0.08
20		10B	0.1	0.00	0.02	0.02	0.04	0.03	0.01	0.11	0.01
21		11A	0.2	0.00	0.04	0.04	0.05	0.05	-0.06	0.10	0.05